



MULTI PROTECT BOARD

| PROPERTIES | UNIT | DATA |
|----------------------------|---------------------|---|
| DENSITY | g / cm ³ | 0,75 ~ 1,20 |
| THICKNESS | mm | 4 mm - 20 mm |
| LENGTH | mm | 2440 / 3000 |
| WIDTH | mm | 1220 / 1000 |
| Combustibility | / | Non-combustible |
| Fire performance | / | A1 (EN13501-1) |
| Fire rating | min | 60 min , E60 : EW60 : EI60 (EN 1364-1:2015) |
| Thermal conductivity | W/(m.k) | ≤0,205 (EN12667:2001) |
| Water absorption | % | ≤ 23 |
| Compressive strength | Mpa | ≥ 12 |
| Modulus of elasticity | Mpa | 2851 |
| Freezing resistance | / | No delamination and no chaps |
| Impact strength | J | 7,52 |
| Thickness tolerance | mm | + - 0,5 mm |
| Tolerance length and width | mm | + - 1,5 mm |
| Alkanity | pH | ≤ 9 |
| Texture | | Smooth, woodgrain |
| Colour | | White |

Other information

This information is furnished without warranty, expressed or implied, except that it is accurate to the best knowledge of Vic International BV. The data on this sheet relates only to the specific material designated herein. Vic International BV assumes no legal responsibility for use or reliance upon this data.

For information regarding specific applications of the product please contact Vic International BV.